



Tychem®

SCIENCE
THAT PROTECTS

6000 F Cat.III


PROTECTION
LEVEL

with dissipative socks
MODEL CHA6

12 | XXXX | 2

1 | **Tychem** with dissipative socks model CHA6 | 3

13 | 6000 F C € 0120 | 4

10 |  | 5

14 | **FLAMMABLE MATERIAL. KEEP AWAY FROM FIRE. DO NOT RE-USE.** | 7

2 | **ВОСПЛАМЕНЯЮЩИЙСЯ МАТЕРИАЛ. ДЕРЖАТЬ ВДАЛИ ОТ ОГНЯ. НЕ ИСПОЛЬЗОВАТЬ ПОВТОРНО.** | 8

6 | **Protective Clothing Category III** | 8

11 | **TYPE 3-B** EN 14605:2005+A1:2009 | 8

9 | **TYPE 4-B** EN 14605:2005+A1:2009 | 8

15 | **TYPE 5-B** EN ISO 13982-1:2004 +A1:2010 | 8

..... **TYPE 6-B** EN 13034:2005+A1:2009 | 8

..... EN 1149-5: 2008 EN 14126: 2003 | 8

..... **EN 1073-2:2002** | 8

..... **Class 1** | 8

..... **Model CHA6 Комбинезон** | 8

..... **EAC** | 8

..... **TP TC 019/2011** | 8

..... **Manufactured by DuPont de Nemours (Luxembourg) s.à r.l. L-2984 Luxembourg** | 8


..... **• DuPont registered trademark Ref.: XXX XXX** | 8

..... **Made in XXX Произведено в XXX** | 8

..... **Other certification(s) independent of CE marking** | 8

..... **Уровень Защиты КК, Щ50, Пм, Нс, Нм, Вн, Ву** | 8

EN • Instructions for Use

BODY MEASUREMENTS CM			
	Size	Chest girth	Body height
	S	84 - 92	162 - 170
	M	92 - 100	168 - 176
	L	100 - 108	174 - 182
	XL	108 - 116	180 - 188
	2XL	116 - 124	186 - 194
	3XL	124 - 132	192 - 200

THE FIVE CARE PICTOGRAMS INDICATE

	Do not wash. Laundering impacts upon protective performance (e. g. antistat will be washed off). • Nicht waschen. Waschen hat Auswirkungen auf die Schutzleistung (z.B. ist der Schutz gegen statische Aufladung nicht mehr gewährleistet). • Ne pas laver. Le nettoyage à l'eau altère les performances de protection (le traitement antistatique disparaît au lavage, par ex.). • Non lavare. Il lavaggio danneggia le caratteristiche protettive (eliminando, ad esempio, il trattamento antistatico). • No lavar: el lavado afecta a la capacidad de protección (p.ej. pérdida del revestimiento antiestático). • Não lavar. A lavagem produzirá impactos no desempenho da proteção (ex.: o efeito anti-estático desaparecerá). • Não lavar. A lavagem produzirá impactos no desempenho da proteção (ex.: o efeito anti-estático desaparecerá). • Tåler ikke vask. Vask påvirker beskyttelseegenskapene (f. eks. vil den antistatiske beskyttelsen vaskes bort.). • Må ikke vaskes. Tørvask påvirker de beskyttende egenskaber (f. eks. vil den antistatiske behandling blive vasket af). • Får ej tvättas. Tvättning påverkar skyddsförmågan (antistatbehandlingen tvättas bort). • Ei saa pestä. Peseminen vaikuttaa suojaustehoön (mm. antistaattisuusaine poistuu pesussa). • Nie prać. Pranie pogarsza właściwości ochronne (np. środek antystatyczny zostanie usunięty podczas prania). • Ne mossa. A mosás hatással van a ruha védőképeségére (pl. az antizstatikus réteg lemosódik). • Neprat. Praní má dopad na ochranné vlastnosti oděvu (např. smývání antistatické vrstvy). • Не пери. Машинното пране въздейства върху защитното действие (например антистатикът ще се отмие). • Neprat. Pranie má vplyv na ochranné vlastnosti odevu (napr. zmyvanie antistatickej vrstvy). • Ne prati. Pranje in likanje negativno učinkujeta na varovalne lastnosti (npr. zaščita pred elektrostatičnim nabojem se spere). • Nu spălați. Spălarea afectează calitățile de protecție (de ex. protecția contra electricității statice dispare). • Не стирайте. Стирка влияет на защитные характеристики (например, смывается антистатический состав). • Neskaltbi. Skalbimas kenkia apsaugai (pvz., nusiplauna antistatinę apsaugą). • Nemazgāt. Mazgāšana var ietekmēt tērpa aizsargfunkcijas. (piem. var nomazgāt antistata pārklājumu). • Mitte pesta. Pesemine mõjutab kaitseomadusi (nt antistaatik võidakse välja pesta). • Yıkamayın. Yıkama, koruma performansını etkiler (örneğin antistatik özelliik kaybolur). • Μην πλένετε τη φόρμα. Το πλύσιμο επηρεάζει την παρεχόμενη προστασία (π.χ. η φόρμα θα χάσει τις αντιστατικές της ιδιότητες).
	Do not iron. • Nicht bügeln. • Ne pas repasser. • Non stirare. • No planchar. • Não passar a ferro. • Niet strijken. • Skal ikke strykes. • Må ikke strykes. • Får ej strykas. • Ei saa silittää. • Nie prasować. • Ne vasalja. • Nežehlit. • He gladji. • Nežehlit'. • Ne likati. • Nu călcați cu fierul de călcat. • Не гладить. • Nelyiginti. • Negludināt. • Mitte triikida. • Ütlemeysin. • Απαγορεύεται το σιδέρωμα.
	Do not machine dry. • Nicht im Wäschetrockner trocknen. • Ne pas sécher en machine. • Non asciugare nell'asciugatrice. • No usar secadora. • Não colocar na máquina de secar. • Niet machinaal drogen. • Må ikke tørkes i trommel. • Må ikke tørretumbles. • Får ej torktumlas. • Ei saa kuivattaa koneellisesti. • Nie suszyć w suszarnie. • Ne szárítsa géppel. • Nesušit v sušiče. • Не суши машинно. • Nesušit v sušičke. • Ne sušiti v stroju • Nu puneti în mașina de uscat rufe. • He подвергать машинной стирке. • Nedžiovinti džiovnykėje. • Neveikt automātiski žāvēšanu. • Árge masinkuivatage. • Kurutma makinesinde kurutmayın. • Απαγορεύεται η χρήση στεγνωτήριου.
	Do not dry clean. • Nicht chemisch reinigen. • Ne pas nettoyer à sec. • Non lavare a secco. • No limpiar en seco. • Não limpar a seco. • Niet chemisch reinigen. • Må ikke renses. • Må ikke kemisk renses. • Får ej kemtvättas. • Ei saa puhdistaa kemiallisesti. • Nie czyścić chemicznie. • Ne tiszttitsa vegyileg. • Nečistit chemicky. • Не почиствай чрез химическо чистене. • Nečistit' chemicky. • Ne kemično čistiti. • Nu curățați chimic. • He подвергать химической чистке. • Nevalyti cheminiu būdu. • Neveikt ķīmisko tīrīšanu. • Árge püüdke puhastada. • Kuru temizleme yapmayın. • Απαγορεύεται το στεγνό καθόρισμα.
	Do not bleach. • Nicht bleichen. • Ne pas utiliser de javel. • Non candeggiare. • No usar lejía. • Não usar lixívia. • Niet bleken. • Må ikke blekes. • Må ikke bleges. • Får ej blekas. • Ei saa valkaista. • Nie wybielać. • Ne fehéritse. • Nebélit. • He избелвай. • Nepoužívat' bielidlo. • Ne beliti. • Nu folosiți înălbitori. • Не отбеливать. • Nebalinti. • Nebalināt. • Árge valgendage. • Çamaşır suyu kullanmayın. • Απαγορεύεται η χρήση λευκαντικού.

ENGLISH

INSTRUCTIONS FOR USE

INSIDE LABEL MARKINGS ❶ Trademark. ❷ Coverall manufacturer. ❸ Model identification - Tychem® 6000F with dissipative socks model CHA6 is the model name for a hooded protective coverall with overtaped seams and cuff, ankle, facial, waist elastication and integrated dissipative socks. This instruction for use provides information on this coverall. ❹ CE marking - Coverall complies with requirements for category III personal protective equipment according to European legislation, Regulation (EU) 2016/425. Type-examination and quality assurance certificates were issued by SGS United Kingdom Ltd., Weston-super-Mare, BS22 6WA, UK, identified by the EC Notified Body number 0120. ❺ Indicates compliance with European standards for chemical protective clothing. ❻ This coverall is antistatically treated inside and offers electrostatic protection according to EN 1149-1:2006 including EN 1149-5:2008 if properly grounded. ❼ Full-body protection "types" achieved by this coverall defined by the European standards for chemical protective clothing: EN 14605:2005 + A1:2009 (Type 3 and Type 4), EN ISO 13982-1:2004 + A1:2010 (Type 5) and EN 13034:2005 + A1:2009 (Type 6). This coverall also fulfils the requirements of EN 14126:2003 Type 3-B, Type 4-B, Type 5-B and Type 6-B. ❽ Protection against particulate radioactive contamination according to EN 1073-2:2002 Class 1. ❾ Wearer should read these instructions for use. ❿ Sizing pictogram indicates body measurements (cm) & correlation to letter code. Check your body measurements and select the correct size. ⓫ Country of origin. ⓬ Date of manufacture. ⓭ Flammable material. Keep away from fire. This garment and/or fabrics are not flame resistant and should not be used around heat, open flame, sparks or in potentially flammable environments. ⓮ Do not re-use. ⓯ Other certification(s) information independent of the CE marking and the European notified body.

PERFORMANCE OF THIS COVERALL:

FABRIC PHYSICAL PROPERTIES

Test	Test method	Result	EN Class*
Abrasion resistance	EN 530 Method 2	> 2000 cycles	6/6**
Flex cracking resistance	EN ISO 7854 Method B	> 1000 cycles	1/6**
Trapezoidal tear resistance	EN ISO 9073-4	> 20 N	2/6
Tensile strength	EN ISO 13934-1	> 100 N	3/6
Puncture resistance	EN 863	> 10 N	2/6
Surface resistance at RH 25%***	EN 1149-1:2006 • EN 1149-5:2008	inside ≤ 2,5x10 ⁹ Ohm	N/A

N/A = Not applicable *According to EN 14325:2004 **Pressure pot ***See limitations of use

FABRIC RESISTANCE TO PENETRATION BY LIQUIDS (EN ISO 6530)

Chemical	Penetration index - EN Class*	Repellency index - EN Class*
Sulphuric acid (30%)	3/3	3/3
Sodium hydroxide (10%)	3/3	3/3
o-Xylene	3/3	3/3
Butan-1-ol	3/3	3/3

* According to EN 14325:2004

FABRIC AND TAPED SEAMS RESISTANCE TO PERMEATION BY LIQUIDS (EN ISO 6529 METHOD A - BREAKTHROUGH TIME AT 1 µg/cm²/min)

Chemical	Breakthrough time (min)	EN Class*
Methanol	> 480	6/6
Chlorobenzene	> 480	6/6
Acetonitrile	> 480	6/6
Toluene	> 480	6/6
n-Hexane	> 480	6/6

* According to EN 14325:2004

FABRIC RESISTANCE TO PENETRATION OF INFECTIVE AGENTS

Test	Test method	EN Class*
Resistance to penetration by blood and body fluids using synthetic blood	ISO 16603	6/6
Resistance to penetration by blood-borne pathogens using bacteriophage Phi-X174	ISO 16604 Procedure C	6/6
Resistance to penetration by contaminated liquids	EN ISO 22610	6/6
Resistance to penetration by biologically contaminated aerosols	ISO/DIS 22611	3/3
Resistance to penetration by biologically contaminated dust	ISO 22612	3/3

* According to EN 14126:2003

WHOLE SUIT TEST PERFORMANCE

Test method	Test result	EN Class
Type 3: Jet test (EN ISO 17491-3)	Pass*	N/A
Type 4: High level spray test (EN ISO 17491-4, Method B)	Pass	N/A
Type 5: Particle aerosol inward leakage test (EN ISO 13982-2)	Pass** • L _{jmm} 82/90 ≤ 30% • L _s 8/10 ≤ 15%***	N/A
Protection factor according to EN 1073-2	> 5	1/3**
Type 6: Low level spray test (EN ISO 17491-4, Method A)	Pass	N/A
Seam strength (EN ISO 13935-2)	> 125 N	4/6****

N/A = Not applicable *Test performed with taped cuffs, hood and ankles **Test performed with taped cuffs, hood, ankles and zipper flap *** 82/90 means 91,1 % L_{jmm} values ≤ 30 % and 8/10 means 80 % L_s values ≤ 15 % ****According to EN 14325:2004

For further information about the barrier performance, please contact your supplier or DuPont: www.ipp.dupont.com

RISKS AGAINST WHICH THE PRODUCT IS DESIGNED TO PROTECT: This coverall is designed to protect workers from hazardous substances, or sensitive products and processes from contamination by people. It is typically used, depending on chemical toxicity and exposure conditions, for protection against certain inorganic and organic liquids and intensive or pressurized liquid sprays, where the exposure pressure is not higher than the one used in the Type 3 test method. A full face mask with filter appropriate for the exposure conditions and tightly connected to the hood and additional taping around the hood, cuffs, ankles and zipper flap are required to achieve the claimed protection. The coverall provides protection against fine particles (Type 5), intensive or pressurized liquid sprays (Type 3), intensive liquid sprays (Type 4) and limited liquid splashes or sprays (Type 6). Fabric used for this coverall has passed all tests of EN 14126:2003 (protective clothing against infective agents). Under the exposure conditions as defined in EN 14126:2003 and mentioned in the table above, the obtained results conclude that the material offers a barrier against infective agents.

LIMITATIONS OF USE: This garment and/or fabrics are not flame resistant and should not be used around heat, open flame, sparks or in potentially flammable environments. Tyvek® melts at 135°C, the fabric coating melts at 98°C. It is possible that a type of exposure to bio hazards not corresponding to the tightness level of the garment may lead to a bio-contamination of the user. Exposure to certain very fine particles, intensive liquid sprays and splashes of hazardous substances may require coveralls of higher mechanical strength and barrier properties than those offered by this coverall. For enhanced protection and to achieve the claimed protection in certain applications, taping of cuffs, ankles, hood and zipper flap will be necessary. The user shall verify that the mask fits the hood design and that tight taping is possible in case the application would require doing so. Care shall be taken when applying the tape, that no creases appear in the fabric or tape since those could act as channels. When taping the hood, small pieces (+/- 10 cm) of tape should be used and overlap. This coverall can be used with or without thumb loops. The thumb loops of this coverall should only be used with a double glove system, where the wearer puts the thumb loop over the under glove and the second glove should be worn over the garment sleeves. For maximum protection, taping of the outer glove to the sleeve must be used. The attached socks of this model are designed to be dissipative and worn inside safety shoes or boots only. The coverall meets the surface resistance requirements of EN 1149-5:2008 when measured according to EN 1149-1:2006, but has the antistatic coating applied to the inside surface only. This shall be taken into consideration if the garment is grounded. The antistatic treatment is only effective in a relative humidity of 25% or above and the user shall ensure proper grounding of both the garment and the wearer. The electrostatic dissipative performance of both the suit and the wearer needs to be continuously achieved in such a way as the resistance between the person wearing the electrostatic dissipative protective clothing and the earth shall be less than 10⁹ Ohm e.g. by wearing adequate footwear/flooring system. If the garment is intended for use in explosive atmospheres, the wearer shall verify the dissipative performance of the garment with socks, a supplementary grounding mechanism may be required, e.g. grounding cable. Electrostatic dissipative protective clothing shall not be opened or removed whilst in presence of flammable or explosive atmospheres or while handling flammable or explosive substances. Electrostatic dissipative protective clothing shall not be used in oxygen enriched atmospheres without prior approval of the responsible safety engineer. The electrostatic dissipative performance of the electrostatic dissipative clothing can be affected by relative humidity, wear and tear, possible contamination and ageing. Electrostatic dissipative protective clothing shall permanently cover all non-complying materials during normal use (including bending and movements). In situations where static dissipation level is a critical performance property, endusers should evaluate the performance of their entire ensemble as worn including outer garments, inner garments, footwear and other PPE. Further information on grounding can be provided by DuPont. Please ensure that you have chosen the garment suitable for your job. For advice, please contact your supplier or DuPont. The user shall be the sole judge for the correct combination of full body protective coverall and ancillary equipment (gloves, boots, respiratory protective equipment etc.) and for how long this coverall can be worn on a specific job with respect to its protective performance, wear comfort or heat stress. DuPont shall not accept any responsibility whatsoever for improper use of this coverall.

PREPARING FOR USE: In the unlikely event of defects, do not wear the coverall.

STORAGE AND TRANSPORT: This coverall may be stored between 15 and 25°C in the dark (cardboard box) with no UV light exposure. DuPont has performed tests according to ASTM D-572 with the conclusion that this fabric retains adequate physical strength over a period of 10 years. The antistatic properties may reduce over time. The user must ensure the dissipative performance is sufficient for the application. Product shall be transported and stored in its original packaging.

DISPOSAL: This coverall can be incinerated or buried in a controlled landfill without harming the environment. Disposal of contaminated garments is regulated by national or local laws.

DECLARATION OF CONFORMITY: Declaration of conformity can be downloaded at: www.safespec.dupont.co.uk.

Additional information for other certification(s) independent of CE marking.

Eurasian Conformity (EAC) - Complies with Technical Regulations of the Customs Union TR TS 019/2011.
Евразийское соответствие (EAC) - Соответствует Техническому регламенту Таможенного союза ТР ТС 019/2011.

Комбинезон
EAC
ТР ТС 019/2011
Уровень Защиты КК,
Щ50, Пм, Нс, Нм, Вн, Ву